



MSP GROUP

16/S, Block 'A' New Alipore, Kolkata 700 053
Phone: (033) 2457 0038 / 3940 Fax: (033) 2458 2239

FERRO ALLOY

CHEMICAL COMPOSITION OF FERRO ALLOY PRODUCTS		
[A]	HIGH CARBON FERRO MANGANESE	
	Mn	(70-75%)
	Si	1.5%
	Phos	0.320
	C	6-8%
	S	0.05 max
	FE	BALANCE
	SIZE	10 MM TO 150 MM (lumps) 0 MM TO 3 MM (fines) 3 MM TO 12 MM (chips)
[B]	SILICO-FERRO MANGANESE	
	Mn	(60-65%)
	Si	15%
	Phos	0.350
	C	2%
	S	0.05 max
	FE	BALANCE
	SIZE	10 MM TO 150 MM (lumps) 0 MM TO 3 MM (fines) 3 MM TO 12 MM (chips)